

PRODUCT NAME

Nano-Gard™ 200 Plus

Nano particle, waterproofing, hydrophobic concrete sealer



MANUFACTURER

Gemite® Products Inc.

Toll Free: 888-4-GEMITE (888-443-6483)

E-mail: techinfo@gemite.com

Web Site: www.gemite.com

USA

160-3480 East Robinson Rd.

Amherst, NY 14228

Phone 888-443-6483

Fax 888-443-6329

CANADA

1787 Drew Road

Mississauga, Ontario L5S 1J5

Phone 905-672-2020

Fax 905-672-6780

FEATURES AND BENEFITS

- water borne
- penetrating
- hydrophobic
- chemically reactive with the substrate
- hardens and waterproofs concrete surface
- breathable
- protects against penetration of water and salts
- chemically resistant to oils, gasoline and hydraulic fluids
- increases chemical resistance of concrete

PRODUCT DESCRIPTION

Basic Use

Nano-Gard 200 Plus is a clear, water borne penetrating sealer, which is used for waterproofing, dustproofing, hardening, moisture and oil proofing of concrete walls, floors, parking garage slabs, walks and driveways. It is mixed with water in ratios varying from 1 to 2 volume parts of water to 1 volume part of *Nano-Gard 200 Plus*. For maximum penetration, the dilution ratio is typically 1 volume part of *Nano-Gard 200 Plus* to 2 volume parts of potable water. For positive or negative side waterproofing on walls and slabs, the hydrophilic *Nano-Gard 200 ST* is applied in the first in one or two coats. Contact Gemite Products Inc. Technical Service for further information.

Composition of Materials

Nano-Gard 200 Plus is based on modified colloidal silica solutions. When properly diluted with water, it penetrates through the capillary pores of concrete and chemically reacts with products of hydration, filling the open pores and closing small voids. On curing the treatment results in formation of hydrophobic particles, providing a highly effective waterproofing in combination with *Nano-Gard 200 ST*, typically applied in the first coat.

Limitations

Nano-Gard 200 Plus provides water repellence. It may cause a slight darkening of the substrate in some instances. Prepare a site test sample for approval by client/architect if the possibility

of darkening is of concern. Keep in mind that the hydrophobic *Nano-Gard 200 Plus* can be applied only in one coat - the hydrophobicity does not allow penetration of the second coat. The hydrophobicity of the surface will disappear in time due to dirt deposited on the floor surface, or dust on wall surfaces, but the water penetration reduction due to the presence of hydrophobic particles in capillary remains. The larger dynamic cracks must be treated separately. Please contact Gemite Technical Service for further information.

Health and Safety

Nano-Gard 200 Plus is nontoxic and nonflammable. Do not take internally; keep out of reach of children. Depending on the degree of alkalinity, (the dilution ratio with water), *Nano-Gard 200 Plus* may irritate or burn the skin and eyes. If contact with skin occurs, wash with soap and water. Harmful if digested. Keep the product out of reach of children. FOR INDUSTRIAL USE ONLY. It is non-hazardous for transportation purposes. Consult MSDS for additional information.

Packaging

Nano-Gard 200 Plus is supplied 20 L (5 USG) containers, or 209 L (55.3 USG drums).

Coverage

For treating concrete walls or slabs *Nano-Gard 200 Plus* is typically mixed with water in volume ratio of 1:2 (One volume part of *Nano-Gard 200 Plus* and two volume parts of water) When mixed with water 1: 2, the typical coverage is 3.7- 4.9 m² per L (150-200 ft² per USG), per one coat of the diluted solution. Use potable water for dilution, providing that a cloudish precipitate does not occur. Otherwise use distilled water for dilution. Typically one or two coats of *Nano-Gard 200 ST* are applied first prior to application of *Nano-Gard 200 Plus*. The above figures are for estimation purposes only. The coverage rate must satisfy the substrate porosity, but do not over-apply *Nano-Gard 200 Plus*.

TECHNICAL DATA

Weight:	1.18 1.20 kg/L, 10.00 lbs/USG
Penetration	3 to 6 mm (1/8 - 1/4 in)
Appearance	Liquid
Color	Clear to hazy white
Odor	Odorless
pH	11- 12
Solubility in water	Miscible

Storage and Transportation

Shelf life of unopened containers is 1 year.

Gemite Products Inc.
October 2011

3 & 7

03064 Concrete Sealers
03055 Concrete Surface Hardeners

INSTALLATION

Surface must be clean and free of dust, dirt, oil and other contaminants. The surface to be treated must be dry to allow good penetration of *Nano-Gard 200 Plus*. All caulking, patching and joint sealing must be installed prior to application of *Nano-Gard 200 ST*. All cracks and junctions between the horizontal slab and vertical walls must be sealed. *Nano-Gard 200 Plus* will not waterproof these. Existing larger dynamic cracks need to be treated (waterproofed) separately. There are different methods of treating these types of cracks, depending on the type of application. Contact Gemite Technical Service for further information. Clean the surface well - a light shotblast or a high pressure water wash 5,000 psi (34 MPa). Dry the surface over night or longer, to get completely dry substrate. The typical application may proceed as follows: Apply the 1st coat of *Nano-Gard 200 ST* mixed with water 1: 2, using a mop, broom or a squeegee and let it dry for 24 hours on horizontal surfaces. Use a low pressure sprayer on vertical (wall) surfaces. Apply the 2nd coat at the same dilution and let dry for 24 hours. pressure wash the surface with water to remove any excess material to avoid a possibility of white surface laitence. When hydrophobic surface is required use hydrophobic *Nano-Gard 200 Plus* in the last coat. For the best waterproofing and chloride penetration protection effect, it is recommended to use two coats of *Nano-Gard 200 ST* and one coat of hydrophobic *Nano-Gard 200 Plus*. Keep in mind, that after application of hy

drophobic *Nano-Gard 200 Plus*, an additional water borne coats (or paints) can't be applied, since the surface will be rendered hydrophobic. Fresh concrete contains free lime, which will slowly react with the penetrating solution to form an insoluble gel, which increases the resistance to wear and penetration of liquids.

MAINTENANCE

No maintenance required.

WARRANTY

A limited, twelve (12) months, Material Replacement Warranty is available. Contact Gemite Technical Service for further information.

TECHNICAL SERVICE

For advice on suitability of *Nano-Gard 200 Plus* for a specific application, specification assistance and application advice contact Technical Services: US (888) 443-6483 or Canada (905) 672-2020.

Short Specification

The penetrating sealer will be water borne nano-particle silica based *Nano-Gard ST 200*, manufactured by Gemite Products Inc., Amherst, NY (Mississauga, Ontario). It shall be applied at a minimum rate of _____ m²/L (ft²)/USG and dilutions as per manufacturer's current Guide Specifications and Application Instructions.