#### PRODUCT NAME

# Nano-Shield<sup>TM</sup> OSP

# **Organic Solvents Protection**

#### **MANUFACTURER**

# Gemite® Products Inc.

Toll Free: 888-4-GEMITE (888-443-6483)

E-mail: techinfo@gemite.com Web Site: www.gemite.com

 160-3480 East Robinson Rd.
 1787 Drew Road

 Amherst, New York 14228
 Mississauga, Ontario L5S 1J5

 Phone 888-443-6483
 Phone 905-672-2020

 Fax 888-443-6329
 Fax 905-672-6780

**CANADA** 

### **FEATURES**

USA

- Resistant to all organic solvents
- Impermeable to all organic solvents
- Resistant to alkali environment
- Fast cure solvent impermeable in 48 hours
- Protects and Oilproofs highly porous concrete
- Waterproofs on Negative & Positive sides
- Nonflammable
- One component (add water only)
- Completely inorganic & environment friendly
- Long working time 30 minutes plus
- Nontoxic
- Easy application

# PRODUCT DESCRIPTION

# Basic Use

Nano-Shield OSP is a completely inorganic coating/topping used primarily as protection of concrete against penetration of organic solvents and emulsified hydrocarbons. It also provides highly effective waterproofing on both, negative and positive sides. It is used mainly in concrete tanks, as a topping or coating on floors, and in secondary containment structures. In combination with Cem-Kote Barrier Coat 100 it can be bonded, by using special procedures, to oil contaminated concrete. Nano-Shield OSP is also used as a waterproofing coating for existing water storage & water treatment concrete structures, digesters, clarifiers and utility vaults. Nano-Shield OSP is suitable for waterproofing of retaining walls, basements, concrete slabs, swimming pools and other concrete structures.

# **Composition and Materials**

*Nano-Shield OSP* is a one component (add water only), completely inorganic composition containing Portland cement, silica fillers and inorganic binders.

### Limitations

*Nano-Shield OSP* develops its resistance to penetration of solvents by wet curing. It must be wet cured for approximately 3 days.



Mix only the amount of material which can be applied within a 30 minutes period of time. *Nano-Shield OSP* must not be used in acidic environments. Do not apply *Nano-Shield OSP* when the temperature is expected to be below 4°C (40° F) or when rain is imminent. The proper surface preparation is essential for successful bond of *Nano-Shield OSP*.

# **Health and Safety**

Nano-Shield OSP is nontoxic and nonflammable. Your skin might be sensitive to cement. We recommend use of rubber gloves. Avoid contact with skin. If contact occurs, flush immediately with water. Seek medical advice if irritation occurs. Harmful if digested. Keep product out reach of children. FOR INDUSTRIAL USE ONLY. Consult MSDS for additional information.

#### Color

**Industrial Gray** 

#### **Packaging**

Nano-Shield OSP Premix is packaged in 22.7 kg (50 lbs.) bags.

#### Yield

Nano-Shield OSP Premix yields 13.2 L (0.47 ft<sup>3</sup>) and the theoretical coverage is 6.6 m<sup>2</sup> @ 2 mm thickness (or 71 ft<sup>2</sup> @ 80 mils thickness). The thickness of application varies depending upon the actual end use. The actual coverage will depend on surface roughness and the thickness applied. The applicator must carry out a sample application to determine the actual coverage for the given substrate, application rate and method of application. Please contact Gemite Products Inc. for further information..

# Storage and Transportation

*Nano-Shield OSP* stored on pallets in a dry, cool area has a shelf-life of 12 months. Packaged 55 bags per pallet.

# TECHNICAL DATA

Compressive Strength (ASTM C109 Modified)	44.8 - 51.7 MPa (6,500 -7,500 psi)
Modulus of Rupture (ASTM C348) 28 days	6.2 - 7.8 MPa (900 - 1,130 psi)
Bond Strength with Concrete (Pull off test)	Greater than the tensile strength of the concrete substrate
Water Vapor Permeance 3 mm (1/8 in) thickness	1.1 metric perms
Hydraulic Permeability	Concrete block coated with Nano-Shield OSP withstands 135 m (443 ft) water head pressure

## INSTALLATION

tain additional information specific to each application and must the surface form rapid drying. When working under tarps at be followed. Contact Gemite's Technical Service for information specific to your application.

# **Surface Preparation**

Remove all loose and deteriorated concrete, laitance, dust, dirt Clean Up and efflorescence. Sandblast or a high pressure waterblast (min. All tools and equipment must be cleaned with water immediate-6,000 psi (410 bar)) should be used.

The active water leaks must be stopped using Fibre-Patch WP (water plug) and deeper surface deterioration repaired with Fibre-Patch OV (overhead). Leave the surface of Fibre-Patch OV rough and wash it thoroughly with high pressure water before application of Nano-Shield OSP. Nano-Shield OSP should be applied within 48 hours after the surface repair.

# **Reinforcing Steel**

Remove all loose rust from any exposed reinforcing steel and WARRANTY apply two coats of Fibre-Prime rustproofing.

## **Crack Treatment**

Any existing cracks must be treated separately using Cem-Kote TECHNICAL SERVICE Flex ST or Cem-Kote Flex Plus.

### Mixing

Mix one bag, 22.7 kg (50 lbs.), with approximately 4.5-5.0 L (1.1-1.3 USG) of water. Use a drill (400-600 rpm) with a mixing paddle. Gradually add the dry material into water and mix until a smooth and lump free mix is obtained. Do not over mix. Adjust the water for brushable consistency or a stiffer consistency for trowel application.

# **Application**

Brush apply Nano-Shield OSP in two consecutive coats to achieve the specified thickness - typically 2-3 mm, (80-120 mils). No wetting is required between the coats. The re-coating must be done within 1/2 to 1 hour. When layers over 3 mm (1/8in) are required, apply a thin layer of Nano-Shield OSP first as a bonding agent by brush or broom. Apply second, stiffer consistency, coat of Nano-Shield OSP into the wet slurry by trowel. Keep wet edge. Do not build up a layer thicker than 6 mm (1/4 in). Follow current manufacturer's Guide Specifications, Application Instructions and the specified rate of application.

### Curing

Current Guide Specification and Application Instructions con- Moist cure Nano-Shield OSP for a minimum of 3 days. Protect freezing temperatures, avoid using propane heaters. Electrical heaters should be used to prevent "carbonation" of Nano-Shield OSP

ly after use. Cured material must be removed mechanically.

#### AVAILABILITY AND COST

Nano-Shield OSP is available worldwide. Contact Gemite Products Inc. for the name of the nearest Representative or Distributor and current pricing information.

## **MAINTENANCE**

None required.

A limited twelve (12) month Material Replacement Warranty is available. For details, contact Gemite's head office.

For advice on suitability of Nano-Shield OSP for specific application, specification assistance and application instructions, contact Technical Service: USA 888-443-6483 or Canada 905-672-2020.

# **Short Specification**

The organic solvent resistant, waterproofing coating/topping will be Nano-Shield OSP as manufactured by Gemite Products Inc., [USA 888-443-6483] [Canada 905-672-2020]. It will meet all the Technical Data specified in the current Nano-Shield OSP Product Data Sheet.