# **Reinforcing Fabric HD**<sup>TM</sup> **Reinforcing Fabric Heavy Duty**

# **MANUFACTURER**

## Gemite<sup>®</sup> Products Inc.

| Toll Free: | 888-4-GEMITE (888-443-6483) |
|------------|-----------------------------|
| E-mail:    | techinfo@gemite.com         |
| Web Site:  | www.gemite.com              |

| USA                        |              | CANADA         |                 |  |
|----------------------------|--------------|----------------|-----------------|--|
| 160-3480 East Robinson Rd. |              | 1787 Drew Road |                 |  |
| Amherst, NY 14228          |              | Mississauga,   | Ontario L5S 1J5 |  |
| Phone                      | 888-443-6483 | Phone          | 905-672-2020    |  |
| Fax                        | 888•443•6329 | Fax            | 905•672•6780    |  |

# **FEATURES**

- Superior Alkali Resistance
- Lightweight
- Highly Flexible
- Non-Toxic
- Non-Allergenic
- Superior Impact Strength
- Molds Easily Around Complex Shapes
- Economical

# **PRODUCT DESCRIPTION**

#### **Basic Use**

*Reinforcing Fabric HD* is a woven polymeric reinforcing fabric. It is specifically designed for the reinforcement of *Cem-Kote* Flex line of products manufactured by Gemite Products Inc.

## **Materials and Composition**

with superior durability, resistance to Portland cement and UV resistance.

## Limitations

Do not use Reinforcing Fabric HD with Thermo-Shield NC.

## Health and Safety

Reinforcing Fabric HD is non-toxic and non-allergenic. Keep product out of reach of children. FOR INDUSTRIAL USE ONLY. Consult MSDS for additional information.

## Color

White.

# Packaging

Reinforcing Fabric HD is available in rolls of 25 cm x 38.1 m (10" x 125 ft) and 99 cm x 51.8 m (39" x 170 ft).

## Yield

The yield of the roll is  $m^2$  ( $ft^2$ ). The actual yield will be lower due to overlaps (see Specification).

## **Storage and Transportation**

Reinforcing Fabric HD, stored in dry and cool area, has virtually unlimited shelf life.



# **TECHNICAL DATA**

| Value                                 | Imperial Units        | S.I. Units          |
|---------------------------------------|-----------------------|---------------------|
| Construction                          | 12 x 5.6 end/in       | 4.7 x 2.2 ends/cm   |
| Mass per Area<br>ASTM D <b>-</b> 5261 | $2.6 \text{ oz/yd}^2$ | 88 g/m <sup>2</sup> |
| Tensile Strength<br>ASTM D-4632       | 60 x 50 lbs           | 267 x 223 N         |
| Tensile Elong.<br>ASTM D-4632         | 30%                   | 30%                 |
| Mullen Burst<br>ASTM D-3786           | 110 psi               | 758 kPa             |
| Aperture Size                         | 0.16 x 0.19 in        | 4.1 x 4.8 mm        |
| Stiffness<br>ASTM D-1388              | 50 in lbs             | 57.7 kg cm          |
| Color                                 | White                 |                     |

# **INSTALLATION**

Current Guide Specification and Application Instructions contain additional information specific to use of Reinforcing Fabric HD in applications of Thermo-Shield FC System and Cem-Kote Flex products and must be followed.

# AVAILABILITY AND COST

Reinforcing Fabric HD is made of a high quality polymeric fiber Available worldwide. Contact Gemite Products Inc. for the name of the nearest Representative/Distributor and current pricing information.

## MAINTENANCE

None required.

## WARRANTY

A limited twelve (12) month Material Replacement Warranty is available. For complete details contact Gemite's Head Office.

# **TECHNICAL SERVICE**

For technical advice on suitability of Reinforcing Fabric HD for specific application, specification assistance and application advise, contact Gemite Technical Service at: USA 888-443-6483, Canada 905-672-2020.

# **Short Specification**

The reinforcing will be Reinforcing Fabric HD manufactured by Gemite Products Inc. [USA 888-443-6483] [Canada 905-672-2020]. It shall be applied in accordance with manufacturer's current guide specifications and applications instructions. Contact Gemite Products Inc. for specification assistance and application instructions.