PRODUCT NAME

Reinforcing Fabric NCTM Thermo-Shield NC Reinforcing Fabric

MANUFACTURER

Gemite® Products Inc.

Toll Free: 888-4-GEMITE (888-443-6483)

E-mail: techinfo@gemite.com Web Site: www.gemite.com

	CANADA			
160-3480 East Robinson Rd.		1787 Drew Road		
14228	Mississauga,	Ontario L5S 1J5		
888-443-6483	Phone	905-672-2020		
888•443•6329	Fax	905•672•6780		
	14228 888-443-6483	14228 Mississauga, 888-443-6483 Phone		

FEATURES

- Superior Alkali Resistance
- Lightweight
- Highly Flexible
- Non-toxic
- Non-Allergenic
- Superior Impact Strength

PRODUCT DESCRIPTION

Basic Use

Reinforcing Fabric NC is an alkali resistant glass fabric. It is specifically designed to reinforce the Thermo-Shield NC (noncombustible) base coat manufactured by Gemite Products Inc.

Composition and Materials

Reinforcing Fabric NC is made of a high quality glass fiber with surface treatment providing resistance to alkali and superior durability.

Limitations

Reinforcing Fabric NC is used as the reinforcing fabric for WARRANTY Thermo-Shield NC Base Coat.

Health and Safety

Reinforcing Fabric NC is non-toxic and non-allergenic. Keep TECHNICAL SERVICE product out of reach of children. FOR INDUSTRIAL USE For technical advice on suitability of Reinforcing Fabric NC ONLY. Consult MSDS for additional information.

Color

White or Blue.

Packaging

Reinforcing Fabric NC is available in rolls 96.5 cm (38 in) wide by Gemite Products Inc. [USA 888-443-6483] [Canada 905and 45.7 m (150 ft) long.

Yield

The yield of the roll is 44.1 m² (475 ft²). The actual yield will be application instructions. lower due to overlaps (see Specification).



Storage and Transportation

Reinforcing Fabric NC, stored in dry and cool area, has virtually unlimited shelf life.

TECHNICAL DATA

Value	Test Method	Imperial Units	S.I. Units
Construction	ASTM D579	Warp 2.5/in Weft 2.5/in	9.84/10 cm 9.84/10 cm
Tensile Strength	ASTM D638	Warp 160 lbs/in Weft 250 lbs/in	710 N/2.54 cm 1150 N/2.54 cm
Weight	ASTM D579	4.5 oz/yd ²	152 g/m ²
Thickness	Measured	0.023"	0.58 mm
Color		White or blue	
Flexibility	Meets EIMA S resistance.	tandard 101.91, Sec	tion 6.3 for alkali

INSTALLATION

Current Thermo-Shield NC Guide Specification and Application Instructions contain additional information specific to use of the *Reinforcing Fabric NC* and must be followed.

AVAILABILITY AND COST

Available worldwide. Contact Gemite Products Inc. for the name of the nearest Representative/Distributor and current pricing information.

MAINTENANCE

None required.

A limited twelve (12) month Material Replacement Warranty is available. For complete details contact Gemite's Head Office.

for specific application, specification assistance and application advise, contact Gemite Technical Service at: USA 888-443-6483, Canada 905-672-2020.

Short Specification

The reinforcing will be Reinforcing Fabric NC manufactured 672-2020]. It shall be applied in accordance with manufacturer's current guide specifications and applications instructions. Contact Gemite Products Inc. for specification assistance and